



Description

Nilifam 921-SG is designed for use as a stoving paint with high performance intermediate coat based on alkyd-melamine solvent base resin.

Nilifam 921-SG can be applied as an intermediate on carbon steel surfaces.

Recommended use

Adhesion	Good to manually prepared surfaces.
Corrosion resistance	Good for medium to severe conditions
Temperature resistance	Dry: Maximum 200°C

Physical constants

Colours/shade:	RAL NO
Finish:	Semi Gloss
Volume solids, %:	50±5
Theoretical spreading rate:	7 m ² /lit-60 Mic.
Flash point:	35°C
Specific gravity:	1.40±0.15 Kg/l
Dry to touch:	Max. 1 hour at 20°C
(Initial)	
Hardness:	After heating exposure
Fully cured:	After heating exposure
VOC content:	Max. 360 g/l

Application details

Conditions	Do not apply when relative humidity exceeds 80% or when the surface to be coated is less than 3°C above the dew point.		
Method	Airless spray	Air spray	Brush (touch-up)
Thinner (max. vol.)	NF-T-10 (10%)	NF-T-10 (20%)	NF-T-10 (5%)
Spray setting			
Pump ratio minimum	40:1		
Tip size	021"	1.6 mm	
Tip pressure	150 bar/2200 Psi	4-5 bar	
	(Airless spray data are indicative and subject to adjustment)		
Cleaning of tools	NF-T-10		
Indicated film thickness, dry	50 microns		
Indicated film thickness, wet	100 microns		

NILOVEN
NF-921-SG
Curing Agent: None



Packaging (typical)	Mass (Kg)	Size of containers (litres)
Niloven	200	200

Storage & handling

The product must be stored in accordance with national regulations. Keep the containers in a dry, cool, well ventilated space and away from sources of heat and ignition. Containers must be kept tightly closed. Handle with care.

Shelf-life

Niloven	6 month(s)
---------	------------

In some markets commercial shelf life can be dictated shorter by local legislation. The above is minimum shelf life, thereafter the paint quality is subject to re-inspection.

Caution

This product is for professional use only. The applicators and operators shall be trained, experienced and have the capability and equipment to mix/stir and apply the coatings correctly and according to Nilifam's technical documentation. Applicators and operators shall use appropriate personal protection equipment when using this product. This guideline is given based on the current knowledge of the product. Any suggested deviation to suit the site conditions shall be forwarded to the responsible Nilifam representative for approval before commencing the work.

Safety

Handle with care. Before and during use, observe all safety labels on packaging and paint containers, consult Nilifam material safety data sheets and follow all local and national safety regulations. Harmful or fatal if swallowed; immediately seek medical assistance. Avoid inhalations of possible solvent vapors or paint mist, as well as paint contact with skin and eyes. Apply only on well-ventilated areas and ensure that adequate forced ventilation exists when applying paint in confined spaces or when the air is stagnant. Always take precautions against the risks of fire and explosions

Tools and equipment

